

DIVYOL TRANS-30 & 40

DIVYOL TRANS-30 & 40 is an **Uninhibited Transformer Oil** meeting IEC 296 Class I & II: 1982 Standard Specification. It also meets the ASTM D 1275 B Test requirement for Corrosive Sulphur.

Sr. No.	Characteristics	Unit	Test Method	Specification of DIVYOLTRANS-30-IC-296- I (IEC 296 Class I)	Specification of DIVYOLTRANS-40-IC-296- II (IEC 296 Class II)
1	Appearance		Representative sample of the oil shall be examined in transmitted light under a thickness of 10 cm at ambient temperature	Clear free from sediment and suspended matter	Clear free from sediment and suspended matter
2	Density at 20° C (Max)	kg / dm ³	ISO 3675	0.895	0.895
3	Kinematic Viscosity	mm ² / sec	ISO 3104		
	a) at 40° C (Max)			11	11
	b) at -30° C (Max)			No General Requirement	1800
	c) at -15° C (Max)			800	No General Requirement
4	Flash Point, PMCC (Min)	°C	ISO 2719	140	140
5	Inter Facial tension at 25° C (Min)	N / m	ISO 6275	0.04	0.04
6	Electric Strength Breakdown Voltage (BDV)		IEC 156		
	a) As Delivered (Min)	kV		30	30
	b) After treatment (Min)	kV		50	50
7	Dielectric Dissipation Factor (Max) tanDelta at 90° C & 40 to 62 Hz		IEC 247	0.005	0.005
8	Corrosive Sulphur Copper Strip, at 140° C, for 19 Hrs Copper Strip, at 150° C, for 48 Hrs		ISO 5662 ASTM D 1275 B	Non Corrosive No General Requirement	Non Corrosive Non Corrosive
9	Anti Oxidant Additives	%	IEC 666	Not Detectable	Not Detectable
10	Oxidation Stability at 100° C, for 164 Hrs		IEC 74		
	a) Neutralization Value (Max)	mg KOH/gm		0.4	0.4
	b) Sludge (Max)	%		0.1	0.1
11	Pour Point (Max)	°C	ISO 3016	- 30	- 45
12	Neutralization Value (Max)	mg KOH/gm	7.7 of IEC 296	0.03	0.03
13	Water Content	ppm	IEC 733		
	a) Bulk (Max)			30	30
	b) Drum (Max)			40	40

(Revision # 01 dated 19th June,2018)

Disclaimer: Gandhar makes no warranties, representation or conditions of any kind expressed or implied for use with respect to these products. Final determination of suitability of the product for the application contemplated by the users is solely their responsibility.